

Introduction to *ab-initio* methods for EXAFS data analysis

F. d'Acapito
ESRF - GILDA CRG
CNR-INFM-OGG 6, Rue Jules Horowitz F-38043 Grenoble

dacapito@esrf.fr

April 25, 2007


Contents

1	Data analysis methods	2
2	X-ray absorption cross section	4
2.1	General formulation	4
2.2	The Multiple Scattering approach	6
2.3	Other terms in the EXAFS expression	10
2.4	Generalization of the parameters	11
2.5	Computing theoretical terms	13
3	Overview of the UWXAFS package	14
4	ATHENA	17
4.1	Operations carried out by ATHENA	19
4.2	Pre-edge subtraction	20
4.3	Edge position determination	21
4.4	Atomic background subtraction	22
4.5	Edge step determination	23
5	TKATOMS	25
6	FEFF	32
6.1	Modules	34
6.2	Cards	35
6.3	Scattering paths in Feff	36
6.4	Output Files	40

7	ARTEMIS	46
7.1	Metallic Cu, I^{st} shell	47
7.2	Error analysis	56
7.3	Multiple Scattering analysis	57
7.4	Comparison with known physical data	67
7.5	A tetrahedral compound: crystalline Ge	68
8	Conclusion	69

1 Data analysis methods

In an EXAFS experiment, the absorption coefficient μ is collected:



but only the oscillating part contains the information on the local structure like coordination numbers, bond lengths, bond length distribution [1].

The quantitative analysis method consists in:

- Extract the Oscillating part (χ function) from the absorption μ .
- Filter the desired signal χ
- Fit the χ to a suitable model

Consider the basic EXAFS formula:

$$\chi(k) = S_0^2 \frac{NA(k)}{kR^2} e^{-\frac{2R}{\lambda}} \sin(2kR + \phi(k) + \phi_c) e^{-2k^2\sigma^2} \quad (1)$$

The **conventional** way of analyzing EXAFS data is to use empirical standards, often in conjunction with Fourier filter techniques.

In this approach, an *unknown* structure (**blue parameters**) is studied by extracting the **backscattering parameters** from the experimental spectrum of a *known* model compound.

In this lecture, the use of *ab-initio* methods and in particular the University of Washington XAFS package (UWXAFS) in EXAFS analysis based on theoretical standards will be discussed. This method uses theoretical calculations to provide the **red parameters** and has to be used in a variety of cases, namely:

- no empirical standards are available
 - non-resolved shells (BCC 1 – 2nd shell)
 - complex structures
- strong Multiple Scattering effects involved
 - collinear configurations (FCC 4th shell)

2 X-ray absorption cross section

2.1 General formulation


When measuring the X-ray absorption coefficient we measure the (mainly) dipole mediated transition of an electron from a deep core state $|i\rangle$ to an unoccupied state $|f\rangle$. From the Fermi Golden Rule

$$\mu(E) \propto \sum_{f}^{E_f > E_F} \langle f | \hat{\epsilon} \cdot \mathbf{r} | i \rangle^2 \delta(E_f) \quad (2)$$

There are two ways to solve this equation [2]:


- Find an expression for $|i\rangle$ and $|f\rangle$ and evaluate directly the integral.
- Use the Green function method where only the potential and the initial state are needed

Amplitude of the photoelectron wave: a simple derivation.




$$e^{i\delta} \frac{e^{ikR}}{kR} \cos\Theta$$

(3)




$$e^{i\delta} \frac{e^{ikR_i}}{kR_i} \cos\Theta$$

(4)



$$e^{i\delta} \frac{e^{ikR_i}}{kR_i} T(k) e^{i\beta} \frac{e^{ikR}}{kR} \cos\Theta$$

(5)



$$e^{i\delta} \frac{e^{ikR_i}}{kR_i} T(k) e^{i\beta} \frac{e^{ikR_i}}{kR_i} e^{i\delta} \cos\Theta$$

(6)

2.2 The Multiple Scattering approach

In the Green function method the X-ray absorption cross section is written as [3],[4], [5]:

$$\mu(E) \propto -\frac{1}{\pi} \Im \langle i | \hat{\epsilon}^* \cdot r G(r, r', E) \hat{\epsilon} \cdot r' | i \rangle \Theta(E - E_F) \quad (7)$$

Where:

$$G(r, r', E) = \frac{1}{E - H + i\eta}$$

(E= photon energy, H = one-particle Hamiltonian)

That can be explicitated as [4]:

$$\mu(E) \propto \mu^{at} \Im \left\{ \frac{1}{\sin^2 \delta_{L_0}^0} \frac{1}{2^{L_0+1}} \sum_{m_0} [T((1 - GT)^{-1})_{L_0, L_0}^{0,0}] \right\}$$

Where:

T= Atomic Scattering matrix

G Propagator matrix

$$T = \begin{pmatrix} t_0 & 0 & \dots \\ 0 & t_1 & \dots \\ \vdots & \vdots & \ddots \end{pmatrix}$$

$$G = \begin{pmatrix} 0 & G_{0,1} & \dots \\ G_{1,0} & 0 & \dots \\ \vdots & \vdots & \ddots \end{pmatrix}$$

Scattering from i^{th} atom

Propagation from i^{th} to j^{th} atom

The $(1 - GT)^{-1}$ term can be approximated by a serie expansion

$$T(1 - GT)^{-1} \approx \sum_n [T(GT)^n]$$

Yelding:

$$\mu(E) \propto \mu^{at} \Im \left\{ \frac{1}{\sin^2 \delta_{L_0}^0} \frac{1}{2^{L_0+1}} \sum_{m_0} \underbrace{\sum_n [T(GT)^n]_{L_0, L_0}^{0,0}}_{MultipleScattering} \right\} \quad (8)$$

Physical meaning of the various terms:

Note: '0' Indicates the absorber, i and j neighbors.

Math term	Picture	Meaning
$T_0 G_{0,i} T_i G_{i,0} T_0$		Single Scattering
$T_0 G_{0,i} T_i G_{i,j} T_j G_{j,0} T_0$		Double Scattering
⋮	⋮	⋮

The convergence of the serie in (8) is achieved under strict conditions on the energy range and scattering amplitudes (see [3]). Moreover (8) is not generally reducible to a simple analytical expression. However it has been found [5], [6] that each of the various terms of the expansion of (8) can be written as:


$$\chi_{\Gamma}(k) = \left(S_0^2 e^{-2\sigma^2 k^2} \right) \Im \left(\frac{f_{eff}}{kR^2} e^{2i(kR+\phi)} \right) \quad (9)$$

Here Γ is the path index and f_{eff} and ϕ are the effective amplitude and phases of the path under analysis. These quantities can be thus calculated separately and then introduced in a fitting procedure.

2.3 Other terms in the EXAFS expression

$$\chi(k) = S_0^2 \frac{NA(k)}{kR^2} e^{-\frac{2R}{\lambda}} \sin(2kR + \phi(k) + \phi_c) e^{-2k^2\sigma^2} \quad (10)$$


- The Debye-Waller Factor σ^2
- The Photoelectron Mean free path λ
- The Many Body amplitude reduction factor S_0^2




The electron mean free path in solids.

2.4 Generalization of the parameters


When using the Multiple Scattering formalism we must adopt a generalized definition of the variables N , R and σ^2 .



In the case of a 3 centers configuration N becomes the number of triangles per absorbing atom in the structure. Clockwise and counterclockwise are counted separately. In this case $N_3 = 8$.



In a MS path the path length R becomes the half length of the roundtrip. In the present case $R = 4.367 \text{ \AA}$




In a MS path the Debye -Waller factor is defined as follows:

$$\sigma_j^2 = \frac{1}{4} \langle [\sum_{i=1}^{n_j} (\vec{u}_i - \vec{u}_{i+}) \cdot \hat{R}_{ii+}]^2 \rangle \quad (11)$$

2.5 Computing theoretical terms

Here we describe the steps in the generation of theoretical paths:

1.




Compute atomic potentials and phase shifts

Use neutral, free, atomic spheres to construct a muffin tin potential. The embedded atoms are spherical and the interstitial region is flat.

Find all scattering geometries in a cluster


2. Use a heap to construct successively higher orders of MS paths. In this way *all* possible scattering geometries are found in a cluster up to a specified order.



Compute the contribution from each path


Using the list of enumerated paths and the atomic potentials, compute the curved-wave, effective scattering amplitudes and phase shifts for all paths. Polarization is considered *a priori* for all paths.

3.



3 Overview of the UWXAFS package

The package UXWAFS [7] contains all the programs necessary to the generation of the theoretical paths, signal extraction and fit. Here you find [a flowchart of the package](#):



The UWXAFS package is made-up of 4 main programs

(TK)ATOMS Atoms takes the crystallographic data of the compound of interest and generates a suitable file for the program Feff. The file contains the atomic coordinates in the crystal up to a certain distance from the absorber and some control cards for Feff

FEFF Starting from the atomic coordinates Feff calculates the amplitude and phases of scattering paths up to a given order and 'intensity'.

AUTOBK (ATHENA) Used to extract EXAFS $\chi(k)$ part from the absorption spectrum

FEFFIT (ARTEMIS) Fits the EXAFS spectrum with a theoretical model based on the paths calculated by Feff.

Making a [comparison with another package](#) (*GNXAS*) we can here resume sinoptically the operations of the various programs:


UWXAFS	GNXAS	Operation
TKATOMS	CRYMOL, GNPEAK	Atomic coordinates generation
FEFF	GNPEAK, GNXAS	Path search and signal calculation
ATHENA	No analogous	EXAFS signal extraction
ARTEMIS	FITHEO	Signal fitting

Here we will provide a brief introduction to the use of the package. For a complete description and program manuals refer to the project home page [7] on the Web.

4 **ATHENA**

The ATHENA code is used to subtract the atomic background from the raw absorption spectrum and yields the oscillating χ EXAFS function. Here we show a typical screenshot from ATHENA: the page contains all the necessary fields to adjust the subtraction routine to the current data. It is based in the AUTOBK routine that shapes the atomic absorption spline function by minimizing the Fourier Transform amplitude of the subtracted data under a given R_{bkg} value. R_{bkg} is typically taken about 1.0 Å.

The main window of the ATHENA program




4.1 Operations carried out by ATHENA


- Pre-edge subtraction
 - Pre edge Range x to y
- Edge Position determination
 - E0
- Atomic background subtraction
 - Rbkg
 - k-weight
 - Spline Range k x to y
 - Spline Range E x to y
- Edge step determination
 - Normalization Range x to y

4.2 Pre-edge subtraction

ATHENA carries out a linear approximation to the pre-edge region between the **Pre-edge region** limits.




A **G O O D** pre-edge subtraction




A **B A D** one.

4.3 Edge position determination

ATHENA calculates the derivative of the absorption coefficient $\frac{\delta\mu}{\delta E}$ and sets the edge position on the **First maximum**. The results is written in the Eo field.




A **G O O D** Edge determination




A **B A D** one.

4.4 Atomic background subtraction

ATHENA approximates the atomic background via a spline function. This function minimizes the residual in R space for frequencies below Rbkg.




A **G O O D** Edge determination




A **B A D** one.

4.5 Edge step determination

ATHENA approximates the post-edge region by a quadratic function. It is used to extrapolate the value of the absorption coefficient to E_0 . The limits of the function are defined in the **Normalization Range** fields.




A **G O O D** Edge determination




A **B A D** one.

The result of a good spectrum extraction is shown below:



The $\chi(k)$ function oscillates symmetrically around the zero line.



There are no peaks in the Fourier Transform at low (< 1 \AA) R values.

5 TKATOMS

In order to generate the correct EXAFS signals it is mandatory to start from a system with electron densities, bond distances and angles as much similar as possible to the sample in analysis.

For (strained, doped, ...) crystals the starting model will be the (undistorted, undoped, ...) crystal, for amorphous samples it is preferable to use a crystalline compound with similar composition.

The instructions for the program are loaded in the program interface page: see here an example for metallic Cu.

The screenshot shows the TkAtoms software interface. At the top, there are tabs for 'Atoms', 'Absorption', 'Powder', 'DAFS', and 'Plotter'. Below the tabs is a menu bar with 'File', 'Clear', 'Data', 'Preferences', and 'Help'. The main title is 'Atoms: make atomic clusters from crystallographic data'. The interface is divided into several sections:

- Input Parameters:**
 - Cluster Size: 6.00000
 - Shift Vector: 0, 0, 0
 - Output file types: feff
 - IO Fill Gases: N2 (0.00), Ar (0.00), Kr (0.00)
 - Run Atoms button
- Crystallographic Data:**
 - name: copper
 - formula: Cu
 - sites: Cu1
 - refer1: Kittel, ISSP
 - Space Group: f m 3 m
 - Edge: (empty)
 - Parameters: A (3.61000), Alpha, B, Beta, C, Gamma
 - Browse Space Groups button
- Unique Crystallographic Sites:**
 - Number of Sites: 4
 - Add 1 Site button
 - Table with columns: Core Elem., X, Y, Z, Tag, Occ., and Clear buttons.

Core Elem.	X	Y	Z	Tag	Occ.	Clear
1 Cu	0.000000	0.000000	0.000000	Cu1	1	Clear
2	0	0	0		1	Clear
3	0	0	0		1	Clear

It is made up of a series of fields where the details of the crystal (Space group, cell dimension and angles, crystallographic sites) are inserted. These parameters can be found from different sources like:

- R.N.G. Wychoff's *Crystal Structures* [8]. A quite popular book on crystal structures.
- The ICSD database [9] This is a powerful and complete database with more than 76,500 entries in its complete form (needs registration).
- The American Mineralogist database (free access).

You can access this database (<http://icsd.ill.fr>) and enter the details of your structure, namely the elements name and number:

ICSD for WWW - Mozilla Firefox

File Edit View Go Bookmarks Tools Help

http://icsd.ill.fr/icsd/index.php?action=Search&page=1&nb_row=

Customize Links Free Hotmail Windows Media Windows

Authors/Code Years Journal Title/Comment Help
 Elements Element Count Mineral Name ANX Formula Pearson Symbol
 System Laue Class Centering Space Group Cell Size/Mass
 Remarks Min. Distance Distance Select Distance Range Co-ordin.

Search Reset

Query : (EL_COUNT = "1") AND el0.el_symbol = 'Cu'

Select All / None 9 Results References EndNote Details Bonds Pattern Structure

Year	Authors	Struct. Formula	sgr	Mineral Name
<input checked="" type="checkbox"/> 1988	Suh, I.-K.;Ohta, H.;Waseda, Y.	Cu	FM3-M	Copper
<input type="checkbox"/> 1963	Srinavasa Rao, S.;Anantharaman, T.R.	Cu	FM3-M	Copper
<input type="checkbox"/> 1961	Otte, H.M.	Cu	FM3-M	
<input type="checkbox"/> 1953	Swanson, H.E.;Tatge, E.	Cu	FM3-M	Copper
<input type="checkbox"/> 1933	Owen, E.A.;Yates, E.L.	Cu	FM3-M	Copper
<input type="checkbox"/> 1926	Holgersson, S.	Cu	FM3-M	Copper
<input type="checkbox"/> 1925	Westgren, A.;Phragmen, G.	Cu	FM3-M	Copper
<input type="checkbox"/> 1923	Young, J.F.T.	Cu	FM3-M	Copper
<input type="checkbox"/> 1914	Bragg, W.L.	Cu	FM3-M	Copper

Page : [1](9 results) 10 results per page.

Full ICSD database copyright 2003-2005 Fachinformationszentrum (FIZ) Karlsruhe
 PHP/MySQL Interface V05-02-21 copyright 2003-2005 by Peter Hewat email: hewat@free.fr

Done

The database prompts you a list of different structures. You choose that most suited to your investigation and retrieve its the details:

ICSD for WWW : Details - Mozilla Firefox

File Edit View Go Bookmarks Tools Help

http://icsd.ill.fr/icsd/index.php?action=Details&id%5B%5D=59702

Customize Links Free Hotmail Windows Media Windows

ICSD Details

1 entry selected. CC=Collection Code: [mC24]=Pearson Symbol: [d c3]=Wyckoff Symbol: [AuCu3]=Structure Type:

CC=53247 [Help](#) CIF [Export](#) [Bonds](#) [Pattern](#) [Structure](#)


Title	High-temperature expansion of six metallic elements measured by dilatation method and X-ray diffraction.
Authors	Suh, I.-K.; Ohta, H.; Waseda, Y.
Reference	Journal of Materials Science (1988) 23 , 757-760 XRef Also: Annales Academiae Scientiarum Fennicae, Series A6: Physica (1967) 223 , 1-10 XRef
Compound	Cu - [Copper] Copper [cF4] [a] []
Cell	3.613, 3.613, 3.613, 90., 90., 90. FM3-M (V=47.16)
Remarks	: MIN=Copper Cell from 2nd reference: 3.61443 at 296 K, 3.6247 at 449 K, 3.6321 at 550 K, 3.6357 at 607 K, 3.6483 at 779 K

Atom (site)	Oxid.	x, y, z, B, Occupancy					
Cu1	(4a)	0	0	0	0	0	1


Full ICSD database copyright 2003-2005 Fachinformationszentrum (FIZ) Karlsruhe
 PHP/MySQL Interface V05-02-21 copyright 2003-2005 by Peter Hewat email: hewat@free.fr

Done

The same holds for the American Mineralogist database (<http://rruff.geo.arizona.edu/AMS/amcsd.php>). Here's the input page:



And this is the output:



The output of TKATOMS is the *f*eff.inp file that is the input for the following program (feff).

6 FEFF

The Feff program [10], [11] carries out a serie of tasks with the aim of [generating the theoretical signals](#) to be used at the fitting stage. The main actions in a run for EXAFS analysis are listed below:

- Calculation of atomic potentials in the Muffin Tin approximation from the given cluster
- Calculation of the phase shifts
- Analysis of the cluster with identification of the multiple scattering paths
- Calculation of the signals.

All these operations are sequentially done by a serie of *modules*.

Here we show an example of input file *feff.inp*:

```
* This feff.inp file generated by ATOMS, version 2.50
* ATOMS written by and copyright (c) Bruce Ravel, 1992-1999
```

```
TITLE   Cu crystal fcc
EDGE    K
S02     1.0
```

```
*          pot    xsph  fms   paths genfmt ff2chi
CONTROL   1      1     0     1     1     1
PRINT     1      0     0     0     0     3
```

```
*          ixc   [ Vr  Vi ]
EXCHANGE  0      0   0
EXAFS     20
RPATH     11
```

POTENTIALS

```
*  ipot   z [ label   l_scm  l_fms  stoichiometry ]
      0  29   Cu    -1    -1      0
      1  29   Cu    -1    -1      1
```

ATOMS

```
0.00000   0.00000   0.00000   0   Cu1   0.00000
0.00000  -1.80900   1.80900   1   Cu1   2.55831
1.80900   0.00000   1.80900   1   Cu1   2.55831
```

(follow the positions of the atoms up to the 5th shell)

END

6.1 Modules

The calculation proceed as follows: first of all the program is instructed that a K edge spectrum has to be calculated (*EDGE* card). Then the various modules of the program are marked to be run (1) or not (0) in sequence (*CONTROL* card) performing the following operations:

pot Calculates the (atomic, muffin tin) scattering potentials.

xsph Calculates the phase shifts.

fms Full multiple scattering calculation of the absorption cross section. Not used in the present example.

paths path identification

genfmt Scattering amplitude calculation.

ff2chi Output of the various theoretical paths on a file.

6.2 Cards

The card *EXCHANGE* defines the energy-dependent potential type to be used, `ixc=0` corresponding to the complex Hedin-Lunqvist potential.

There are cards that give to the program some limits for the calculation. Here card *EXAFS* limits the maximum k for the calculation to 20 \AA^{-1} , the maximum length (half roundtrip) for a path to be considered in the calculation (*RPATH* card) is 11 \AA and scattering paths up to 4^{th} order ('leg', see next section).


Cards like *SCF*, *XANES*, *FMS*, *LDOS* are created by `tkatoms` and are needed only for a XANES simulations. In an EXAFS analysis will be commented with a `*` character.

Then the program is instructed on how associate the various potentials to the different atoms in the cluster through the *POTENTIAL* card. For different chemical species a different potential number is associated (1, 2, ...) potential 0 is always related to the photoemitter.

Eventually, the *ATOMS* card contains the spatial position and the potential associations are defined for each atom in the cluster.

6.3 Scattering paths in Feff

The scattering order of a path can be defined as the number of lines (legs) you draw between scatterers to describe the process under analysis as shown below:




Here '0' denotes the photoabsorber.

If a same 'loop' (same bonds and angles but different involved atoms except the absorber) is found in different atomic arrangements the associated path is said to be 'degenerate' and the degeneration is calculated and accounted for in the path amplitude. Moreover: the same loop can be run in clockwise or counterclockwise direction: this also is accounted for as a 'degeneration' of the path ¹. These degenerations can be removed when calculating the path amplitude accounting for the polarization (see below).

When considering a given atomic arrangement a **limited number of different paths** have to be considered to correctly account for the its contribution of the total χ signal. For the three atoms 0, i, j a good choice is to consider:

- 0 - i 2 legged path
- 0 - j 2 legged path
- 0 - i - j - 0 3 legged path
- 0 - i - j - i - 0 4 legged path

The importance of the 3 and 4 legged paths grow dramatically as the $0\hat{i}j$ angle approaches 180 deg (i.e. collinear configuration and 0 deg angle scattering on i). As shown in the following picture (Cu atom, plane wave approx. [12])



the modulus of the scattering amplitude $|f(\theta)|$ exhibits a marked maximum at 0 deg (forward scattering).

Finally, couple of points need a particular attention when comparing with the GNXAS code:

- The calculated amplitude of a given MS path is valid only for the geometric arrangement considered. The derivatives of amplitude and phase of the path respect to the path length and path angles are not calculated. This has to be considered when analyzing samples with MS paths exhibiting different geometries with respect to the model, especially for the bond angles.
- For what concerns disorder each path is considered to be damped by a Debye-Waller like factor $e^{-\sigma^2 k^2}$ where σ^2 contains bond length and bond angle disorder (thermal or configurational). There is no explicit separation between the two contributions.

6.4 Output Files

Among the files produced by Feff some of them need particular attention. They are all in ASCII format and can be easily listed for checking:

[feffXXXX.dat](#) This file contains the major parameters of the associated $XXXX^{th}$ path. It looks like this:

```
Cu crystal fcc                      Feff  8.00
Abs   Z=29 Rmt= 1.414 Rnm= 1.460 K  shell
Pot 1 Z=29 Rmt= 1.361 Rnm= 1.398
Gam_ch=1.729E+00 H-L  exch
Mu=-3.268E+00 kf=1.831E+00 Vint=-1.605E+01 Rs_int= 1.980
Path   1  icalc      2
-----
 2 12.000  2.5583   2.6431  -3.26835 nleg, deg, reff, rnmav(bohr), edge
  x   y   z  pot at#
 0.0000  0.0000  0.0000  0  29 Cu  absorbing atom
 0.0000  1.8090  1.8090  1  29 Cu
  k  real[2*phc]  mag[feff]  phase[feff]  red factor  lambda  real[p]@#
0.000  3.6837E+00  0.0000E+00  -5.0825E+00  9.885E-01  1.6150E+01  1.8324E+00
0.100  3.6842E+00  4.9963E-02  -5.5819E+00  9.887E-01  1.6173E+01  1.8350E+00
```

where the various columns contain:

- `k` the photoelectron wavevector
- `real[2*phc]` the central atom phase * 2
- `mag[feff]` the path amplitude
- `phase[feff]` the backscatterer phase
- `phase[feff]` the central atom reduction factor
- `lambda` the photoelectron mean free path
- `real[p]` the real part of the photoelectron momentum

This file is directly usable with the *feffit* program or, suitably manipulated, with a generic EXAFS fitting program.

[list.dat](#) The 'list.dat' file resumes some basic informations on the calculations on the various scattering paths. For each (numbered by 'pathindex' that also gives the name to the corresponding feffXXX.dat file) it is indicated:

- the σ^2 factor considered (if any)
- the amplitude ratio respect to the first path
- the degeneracy (that, in case of single scattering path is the number of neighbors)
- the scattering order
- the effective path length (half the loop length, for single scattering coincides with the bond length).

Here we show a typical output for this file:

Cu crystal fcc Feff 8.00
Abs Z=29 Rmt= 1.414 Rnm= 1.460 K shell
Pot 1 Z=29 Rmt= 1.361 Rnm= 1.398
Gam_ch=1.729E+00 H-L exch
Mu=-3.268E+00 kf=1.831E+00 Vint=-1.605E+01 Rs_int= 1.980

pathindex	sig2	amp ratio	deg	nlegs	r effective
1	0.00000	100.000	12.000	2	2.5583
2	0.00000	23.042	6.000	2	3.6180
3	0.00000	11.967	48.000	3	3.8375
4	0.00000	9.198	48.000	3	4.3673
5	0.00000	55.644	24.000	2	4.4311
6	0.00000	11.632	48.000	3	4.7739
7	0.00000	24.567	96.000	3	4.7739
8	0.00000	19.047	12.000	2	5.1166
9	0.00000	9.492	12.000	3	5.1166
10	0.00000	43.979	24.000	3	5.1166
11	0.00000	8.413	12.000	4	5.1166
12	0.00000	4.189	12.000	4	5.1166
14	0.00000	31.858	12.000	4	5.1166

[path00.dat](#) This file contains a more exhaustive description of the paths permitting their identification. Here is a typical output:

```


Cu crystal fcc
Rmax 11.2566, keep limit 0.000, heap limit 0.000
Plane wave chi amplitude filter 2.50%
-----
  1   2 12.000 index, nleg, degeneracy, r= 2.5583
    x      y      z   ipot label   rleg   beta   eta
0.000000  1.809000  1.809000  1 'Cu   '   2.5583 180.0000 0.0000
0.000000  0.000000  0.000000  0 'Cu   '   2.5583 180.0000 0.0000
  2   2  6.000 index, nleg, degeneracy, r= 3.6180
    x      y      z   ipot label   rleg   beta   eta
0.000000  3.618000  0.000000  1 'Cu   '   3.6180 180.0000 0.0000
0.000000  0.000000  0.000000  0 'Cu   '   3.6180 180.0000 0.0000
  3   3 48.000 index, nleg, degeneracy, r= 3.8375
    x      y      z   ipot label   rleg   beta   eta
-1.809000  1.809000  0.000000  1 'Cu   '   2.5583 120.0000 0.0000
-1.809000  0.000000 -1.809000  1 'Cu   '   2.5583 120.0000 0.0000
 0.000000  0.000000  0.000000  0 'Cu   '   2.5583 120.0000 0.0000
  4   3 48.000 index, nleg, degeneracy, r= 4.3673
    x      y      z   ipot label   rleg   beta   eta
0.000000  3.618000  0.000000  1 'Cu   '   3.6180 135.0000 0.0000
-1.809000  1.809000  0.000000  1 'Cu   '   2.5583  90.0000 0.0000
 0.000000  0.000000  0.000000  0 'Cu   '   2.5583 135.0000 0.0000

```

For each path it is indicated the number, scattering order, degeneracy and length.

The successive numbers are added to better describe the path but are not considered by **genfmt**. *rleg* is the leg length, *beta* indicates the photoelectron scattering angle. Namely for path 4 in the previous example if we start from atom with potential '0' (the absorber at 0.0, 0.0, 0.0) going to the first scatterer the photoelectron travels for 2.558 Å then scatters on the neighbor at (-1.809, 1.809, 0.00) with an angle of 90 deg, travels again for 2.558 Å scatters of 135 deg on the neighbor at (0.0, 3.618, 0.0) and travels for 3.618 Å before coming back to the absorber.

The picture below describes path 4 with bond lengths and angles evidenced.



7 ARTEMIS

For data fitting we have the the ARTEMIS code. ARTEMIS takes the experimental $\chi(k)_{exp}$ function and compares it with a theoretical $\chi(k)_{teo}$ function that is build-up using the theoretical EXAFS paths previously calculated with Feff.

Then it creates a difference function Ξ as follows

$$\Xi = \frac{1}{w} \sum_{i=kpoints} (\chi(k^n)_i^{exp} - \chi(k^n)_i^{teo})^2 \quad (12)$$


$\chi(k)_{teo}$ is a function of the structural parameters

$$\chi(k^n)_{teo} = \chi(k^n, N, R, \sigma, \Delta E_0)_{teo} \quad (13)$$

The fitting routine varies these parameter in order to minimize the Ξ function.

7.1 Metallic Cu, I^{st} shell

The picture below presents the input page:




ARTEMIS needs the following inputs:

- an experimental $\chi(k)$ spectrum, extracted (namely) with ATHENA.
- the feffxxxx.dat theoretical paths generated by feff

Successively, the details for FT transformation and fit have to be added like:

- *krange* The range in k space for FT
- *kweight* n in the k^n weight for exp. data
- *dk* The 'width' of the window
- *kwindo* The window type (see manual)
- *R-range* The fit range in R space (if used)
- *Fitting space* Can be k, R or q.


The theoretical paths to be used for the fit can be added under the menu **FEFF** → **Add a feff path** and a window pops up with the details of the path:



For each path (only one in this case) a name for each variable has to be chosen to be used in the following section. In this case we considered the number of neighbors 12 so we decide to fit:

- the S_{02} parameter, amp
- the edge shift E_0 , e_0
- the deviation from the theoretical bond length delR , $\text{reff}*\text{delR}$
- the Debye-Waller factor ss_2 , ss .


Finally the *user variables* to be fitted are declared with the **guess** or **set** commands with their initial values:




Set can be also used to define relations between the variables that represents one of the major points of the *ARTEMIS* program. This permits to reduce the free parameters by introducing a little physics in the problem.

Eventually clicking the **FIT** button starts the fit. ARTEMIS uses equation (10) to fit data in a given R range. In this way only paths with a length less than R have to be considered in the fit permitting the analysis on a limited frequency region of the spectrum.

The results of the fits are shown below:



The R space fit.



The q space fit.

The results of the fits are written in the file **.log*

Project title : Fitting cu50kk.chi
Prepared by :
Contact :
Started : 14:07:30 on 13 April, 2007
This fit at : 14:18:33 on 13 April, 2007
Environment : Artemis 0.6.009 using Windows XP, perl 5.006001, Tk 800.023, and Iffffit 1.2.5

=====

Independent points	=	15.845703125
Number of variables	=	4.000000000
Chi-square	=	11.856670253
Reduced Chi-square	=	1.000925832
R-factor	=	0.002451116
Measurement uncertainty (k)	=	0.000630000
Measurement uncertainty (R)	=	1.471120523
Number of data sets	=	1.000000000

Guess parameters +/- uncertainties:

amp	=	0.8705065	+/-	0.0257853
e0	=	5.7637639	+/-	0.4419175
delr	=	-0.0013737	+/-	0.0005666
ss	=	0.0035691	+/-	0.0001233

Explicit data on the various paths (namely r and σ^2) are shown in the remainder of the **.log* file

```
===== Paths used to fit cu50k.chi
```

```
FEFF0: feff0001.dat (ifeffit group = feff0_1)
```

```
feff      = C:\DOCUMENTS\PRESENTAZIONI\07-ARS2\EXERCISES\CU\TEO\feff0001.dat
id        = reff = 2.5527, degen = 12.0, path: Cu->Cu->Cu
r         = 2.549193
reff      = 2.552700
degen     = 12.000000
n*s02     = 0.870506
e0        = 5.763764
dr        = -0.003507
reff+dr   = 2.549193
ss2       = 0.003569
```


As a general rule in the first part the results on the 'fitted' variables are resumed together with the statistical analysis of the fit (χ^2 analysis, error analysis, correlations, ...).

Then the fit conditions (weight, boundaries, ...) are shown.

Finally the results on the path variables are resumed. Note a few tricks:

- Take care to the relations you established between path and user variables.
- For the bond length R the actual fitted variable is delR. To know the R value you have to see the value of {reff + delR}
- *ARTEMIS* considers by default the path with its geometrical degeneracy. So in this case we got 12 neighbours (degen) without explicitly telling the program as it went from the calculation. If the number of neighbors is your unknown you have to run the program with the N card = 1 and attribute to each path an amplitude $S_0^2 \times N$ where S_0^2 is found from a reference compound and N is the number of neighbors to be fitted.


7.2 Error analysis

A few considerations now on the error analysis made by *ARTEMIS*. The fitting routine works through the [minimization of a \$\chi^2\$ -like function](#). For the correct statement of such a function (in order to perform a statistical analysis on it) it is mandatory to correctly determine the noise [Epsilon](#) on the data. When working in Fourier Transformed space it is hard to establish a relation between the noise you can estimate on the spectrum (by the square root of counts or by empirical techniques) and the error that propagates through the fourier filter. An accurate error analysis is necessary to:

- decide whether what we have found is a good fit or not
- attribute error bars to the best-fitting quantities

ARTEMIS has an [automatic routine that determines the 'noise'](#) on the data from the residual extracted from the Fourier Transformed data between $R = 15 - 25$ Å. In this way values of the χ_ν^2 (χ -square function divided by the number of free parameters ν) well above 1 are obtained even for the best looking fits, preventing a correct statistical analysis. *ARTEMIS* circumvents this problem by calculating the parameters uncertainties by multiplying the square root of the diagonal elements of the correlation matrix by $\sqrt{\chi_\nu^2}$. This is equivalent to rescale [Epsilon](#) to obtain a $\chi_\nu^2 = 1$ that is to assume *a priori* the goodness of the fit and attributing to statistical *noise* the misfit.

7.3 Multiple Scattering analysis



In the Fourier Transform of the metallic Cu foil several coordination shells are well visible above the first.

pathindex	sig2	amp ratio	deg	nlegs	r effective
1	0.00000	100.000	12.000	2	2.5527
2	0.00000	23.055	6.000	2	3.6100
3	0.00000	12.006	48.000	3	3.8290
4	0.00000	9.191	48.000	3	4.3577
5	0.00000	55.708	24.000	2	4.4213
6	0.00000	11.690	48.000	3	4.7633
7	0.00000	24.544	96.000	3	4.7633
8	0.00000	19.077	12.000	2	5.1053
9	0.00000	9.524	12.000	3	5.1053
10	0.00000	44.354	24.000	3	5.1053
11	0.00000	8.648	12.000	4	5.1053
12	0.00000	4.228	12.000	4	5.1053
14	0.00000	32.552	12.000	4	5.1053


Also from the *feff* calculation (file list.dat) several higher order paths (3 and 4 legged) result to have a considerable amplitude.

A fit of the [higher coordination shells](#) can give a deeper insight in the material structure. Moreover for such task the inclusion of Multiple Scattering (MS) paths is mandatory.

feff has already indicated the [stronger paths](#) to be considered. By constructing our model we only have to avoid [free parameter proliferation](#) due to the increased number of paths.


With *ARTEMIS* path parameters can [easily linked](#) so minimizing the number of free parameters.

Below we show the input page for a 4 shell fit of metallic Cu:




Here the path list includes :


Single scattering paths from the first to the fourth shell (paths 1, 2, 5, 8)




1st Shell (Path 1)




2nd shell (Path 2)




3rd shell (Path 5)




4th shell (Path 8)



Double scattering between absorber and 2 Nearest Neighbors (NN) with the absorber in the vertex of a 60 deg angle (path 3).




Double scattering between the absorber and 2 NN. The absorber is on the vertex of a 120 deg angle (path 6).



Double scattering between the absorber, a 1 NN and a 3 NN (path 7).

- **Double scattering** between the absorber and collinear NN and 4th neighbor, the absorber at an **edge of the chain** (path 10)
- **Triple scattering** back and forth touching all the atoms in a configuration similar to path 10 (path 14)



The grouping of the parameters can be done as follows:

- a `common value of e0 and s02 can be used for all.`
- `an overall scaling of the path lengths` can be done by using the feffit function *reff*. This can be useful when treating global expansion due to doping, temperature, ...It can coupled to the delr variable of all paths with the command:

$$\text{reff} * \text{delR}$$


in this way for each path the length R is calculated as a fraction delR of the theoretical length reff. delR is the only fitting parameter for the bond lengths.

- `Debye-Waller factors` calculated with a `correlated Debye model` [17, 16] using the special function


$$Debye(meas_{temp}, Debye_{temp})$$

. The σ^2 of the firs shell is left free.

Following these prescriptions we end up to fit the spectrum of metallic Cu up to the fifth shell with 10 paths and only 5 free (e0, s02, delR, ss, temp) parameters. The results are shown below:




The R space fit.




The k space fit.

Contribution of the various paths to the total spectrum:



The R space.



The r space.

The results are shown in the *feffit.log* file:

Project title : Fitting cu50kk.chi
Prepared by :
Contact :
Started : 14:07:30 on 13 April, 2007
This fit at : 14:25:09 on 13 April, 2007
Environment : Artemis 0.6.009 using Windows XP, perl 5.006001, Tk 800.023, and Ifeffit 1.2.5

=====

Independent points	=	46.703125000
Number of variables	=	5.000000000
Chi-square	=	41.728342234
Reduced Chi-square	=	1.000604685
R-factor	=	0.012413644
Measurement uncertainty (k)	=	0.000909000
Measurement uncertainty (R)	=	2.122616754
Number of data sets	=	1.000000000

Guess parameters +/- uncertainties:

amp	=	0.9166783	+/-	0.0333725
e0	=	4.6087464	+/-	0.4168785
delr	=	-0.0018688	+/-	0.0005401
ss	=	0.0037685	+/-	0.0001616
temp	=	261.7400839	+/-	8.3454342

7.4 Comparison with known physical data

Parameter	EXAFS result	Literature data
a_0 (Å)	3.603 ± 0.002	3.610
T_{Debye} (° C)	262 ± 8	315

7.5 A tetrahedral compound: crystalline Ge

This is left as an exercise for the students. Here I will only suggest the *atoms.inp* file:

```
\title GE
space DIAMOND a= 5.65735 rmax = 6      core= Ge

out = feff.inp

atom ! Type      x      y      z      tag
  Ge    0.125    0.125    0.125    Ge1
-----
```

Then proceed as follows:

- Calculate the cluster
- Calculate the theoretical paths
- Try a first shell fit
- try a multiple shell (and multiple scattering) fit up to the 3rd shell.

8 Conclusion

Here we have briefly introduced the UWXAFS analysis package for EXAFS data. We warmly recommend the students to further train themselves on well known structures (bcc, zincblende, ...) to gain a full control of the various parts of the program before approaching a *real* unknown sample. Due to its introductory form this lecture is far from being exhaustive so we invite the students to refer to the programs manuals (available on the relative web pages). Another introductory course (to which a lot of pages of the present lecture are inspired) can be find in [20]. For further questions, feel free to contact me at the address: dacapito@esrf.fr.

References

- [1] P.A.Lee, P.H.Citrin, P.Eisenberger and B.M.Kincaid, *Rev. Mod. Phys.* **53** (1981), 769.
- [2] D.C. Koningsberger, R.Prins *X-ray Absorption:Principles, Applications Techniques of EXAFS, SEXAFS and XANES* John Wiley and Sons, New York, 1988.
- [3] C.R.Natoli, M.Benfatto, *J. de Phys. Colloques* **C8** (1986), C8-11.
- [4] A. Filipponi, A di Cicco, C.R.Natoli, *Phys. Rev.* **B52**, (1995), 15122.
- [5] J.J.Rehr, R.C.Albers, *Rev.Mod.Phys.* **72**,(2000), 621.
- [6] J.J.Rehr, R.C.Albers, *Phys.Rev* **B41**,(1990), 8139.
- [7] <http://depts.washington.edu/uwxafs/>
- [8] R.N.G. Wychoff *Crystal Structures* Wiley ed., New York.
- [9] <http://icsd.ill.fr/icsd/>
- [10] S.I.Zabinsky, J.J.Rehr, A.Ankudinov, R.C.Albers, M.J.Eller, *Phys.Rev* **B52** (1995), 2995.
- [11] A.L.Ankudinov, B.Ravel, J.J.Rehr, S.D.Conradson, *Phys.Rev.* **B58** (1998), 7565.
- [12] P.A.Lee, G.Beni, *Phys.Rev.* **B15** (1977), 2862.
- [13] M.Newville, P.Livins, Y.Yacoby, J.J.Rehr, E.A.Stern, *Phys. Rev. textbfB47* (1993), 14126.
- [14] M. Newville, B. Ravel, D. Haskel, J. J. Rehr, E. A. Stern, and Y. Yacoby, *Physica B* **208&209**, p154-155 (1995).
- [15] <http://cars9.uchicago.edu/~newville/feffit/>
- [16] A. Poiarkova, J.J.Rehr *Phys Rev B* **59** (1999), 948.
- [17] E. Sevillano, H.Meuth, J.J.Rehr *Phys Rev B* **20** (1979), 4908.

- [18] P.Eisenberger, G.S.Brown, *Solid State Commun.* textbf29 (1979), 481.
- [19] G. Dalba, P.Fornasini *J.Synch. Rad.* 4(1997), 243.
- [20] <http://leonardo.phys.washington.edu/~ravel/course/Welcome.html>